

**Processed Glass Aggregate
Specs at a Glance
January 2002**

	VT ANR	AASHTO	VTrans
Size	>95% passes 25mm (1") screen, <3% of material passing 4.75mm screen passes 75 μm screen	100% passes 9.5 mm (3/8") screen	Same as VT ANR
Non Beverage Glass	<5% china, plate glass ceramics. No flourescent lights or CRTs	Same as VT ANR	<5% china, plate glass ceramics.
Contaminants	<1% screw tops, plastic rings, paper, labels	<1% screw tops, plastic rings, paper, labels, and <2% "soil-like material"	"trace" of screw tops, plastic rings, paper, labels
Haz. Materials	"The PGA shall contain no hazardous waste."	"Free of ...any toxic or hazardous material."	"Glass containers containing, or having contained, toxic or hazardous materials will not be allowed"
% of PGA in final product	Not specified	Up to 20%	Up to 10%
Allowable Applications	Base course, subbase, embankments. Trench bedding and backfill. Retaining wall backfill, foundation drains, french drains.	"Granular road base material."	"Sand Borrow," "Gravel for Subbase," "Crushed Gravel," "Dense Graded Crushed Stone."